

## ELASTOCOAT™ A-1000 QS ACRYLIC ROOF COATING

### PRODUCT DESCRIPTION:

ELASTOCOAT™ A-1000 QS is a quick setting elastomeric acrylic roof coating. It forms a waterproofing membrane with superior weatherproofing, durability, flexibility, and color retention for long-term protection. A-1000 QS is a single component basecoat / topcoat system designed for easy application with conventional or airless spray equipment, as well as brush and rollers. The A-1000 QS system is economical, reflective, and energy efficient. Please contact the BASF Technical Service Department for further information. A-1000 QS is ENERGY STAR® listed as a reflective roof coating. A-1000 QS is used to protect, weatherproof, and reflect UV radiation when used over spray polyurethane foam systems, built-up roofs, modified Bitumen systems, and metal roof systems. A-1000 QS can also be used as a damp proofing material over masonry and wood surfaces. A-1000 QS is not suitable for interior applications in place of a thermal barrier. This acrylic coating system has excellent adhesion to many other existing coatings and roof surfaces.

TYPICAL PROPERTIES (Liquid):		
Property	Value	Test Method
Solids by Weight:	68%(±2)	ASTM D 4209
Solids by Volume:	55%(±2)	ASTM D 5201
Theoretical Coverage:	882 ft <sup>2</sup> /gal @ 1 mil	
Volatile Organic Content (VOC):	28 g/l	EPA Method 24
Colors:*	Standard white; light & dark gray	
Weight per gallon:	White - 11.7 lbs./gal	ASTM D 1475
	Light & Dark Gray - 11.9 lbs./gal	ASTM D 1475

\* Custom colors are available at an additional cost.

TYPICAL PROPERTIES (Cured):		
Property	Value	Test Method
Cure Rate:		
Time to tack free @ 75°F (24°C), 50%RH	White - 3 hrs; Gray - 2 hrs	
Full Cure @ 75°F (24°C), 50%RH	2 - 3 days	
Tensile Strength:	280 (±20) psi (1.38 MPa)	ASTM D 2370
Elongation:	270% (±20)	ASTM D 2370
Hardness:	55-65 Shore A	ASTM D 2240, C 661
Permeance:	2.7 US Perms @ 20 dry mils	ASTM E 96 (B)
Water Absorption:	1.5% maximum	ASTM D 471
Low Temperature Flexibility:	Passes	ASTM C 734
Accelerated Weathering (3,000 hours):	No Checking, cracking or loss of flexibility	ASTM G 53
Fungi Resistance:	0 rating	ASTM G 21
Fire Resistance:**	Passes UL Class A noncombustible and Class B combustible decks	UL 790

\*\* This fire rating is not intended to reflect hazards present by this or any other materials under actual fire conditions. This data is based on laboratory tests and may not reflect actual in place properties or performance.

# ELASTOCOAT™ A-1000 QS

## ACRYLIC ROOF COATING

**Shipping Weight:** 55 gal Drum White – 684 lbs. 55 gal Drum Gray – 695 lbs

**Storage:** A-1000 QS will freeze and become unusable at or below 32°F (0°C). Do not store or ship unless protection from freezing is assured. Shelf life is approximately 12 months. Store at 65°F - 90°F (18°C - 32°C).

**Freight Classification:** Non-Hazardous/Non-Regulated Product

### Application Instructions:

**Mixing:** A-1000 QS is a single component acrylic coating. It is necessary to mix each container of A-1000 QS with at least a 3/4 hp power agitator for at least 5 minutes prior to use to insure uniform consistency and color.

**Thinning:** Thinning is not normally necessary or recommended. Tap water may be used to reduce the viscosity by thoroughly mixing in up to 5%.

**Methods:** A-1000 QS may be applied by conventional or airless spray equipment or may be applied by brush or roller. Airless spray pumps should develop a minimum of 2,000 psi fluid pressure at 1 gallon per minute output. Use an airless gun with a .027" to .039" spray tip with a fan angle of 40°- 60°. The fluid hose should be a minimum of 3/8" inside diameter up to 100' with greater lengths made up of 1/2" diameter from the spray pump to 300' maximum. Filters should be at least 40 mesh or larger.

**Application:** Polyurethane foam and other surfaces to be coated must be dry and free of all dirt and contaminants. Each coat of A-1000 QS must be tack free before an additional coat is applied. Subsequent coats shall be applied in a direction perpendicular to the previous coat. Additional coats should be applied as soon after the initial coat is tack free and dry to avoid contamination.

Complete cure of the A-1000 QS will take 24-72 hours depending on weather conditions. Lower temperatures and/or high humidity conditions will retard the cure. Do not apply if weather conditions will not permit cure before rain, dew, fog or temperatures below 50°F(10°C) occur. A-1000 QS will cease the curing process when it is below 50°F(10°C). Do not apply in the late afternoon if heavy moisture condensation or rain may occur during the night.

Do not apply without adequate air exchange and ventilation in enclosed areas.

**Clean-up:** A-1000 QS can be cleaned from spray equipment and rollers with clean tap water. It is not recommended to leave the A-1000 QS in the hoses or pumps after or between uses.

### Handling and Safety:

**For specific information refer to OSHA guidelines and the A-1000 QS Material Safety Data Sheet.**

Avoid breathing of vapor or spray mist. For exterior applications, approved (MSHA/NIOSH) chemical cartridge respirators must be worn by the applicator and personnel in the vicinity of the application and a change out schedule must be maintained for the cartridges and respirators. Interior applications require a positive feed fresh air mask and exhaust ventilation.

In case of eye contact, flush with large amounts of water and get medical attention. For skin contact, wipe off liquid and wash affected area with soap and tap water. Remove contaminated clothing and wash before reuse. In the case of ingestion, drink plenty of water and seek medical attention immediately.

**Clean-up of Spills or Leakage:** With adequate ventilation and appropriate personal protective equipment, cover the spill area with an inert absorbent material such as clay or vermiculite and transfer to steel waste containers.

### LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY:

Various Special Warranties may be purchased from BASF Corporation. These include Full System Limited Warranties for 5 to 20 years and Coating-Only Limited Warranties for 5 to 20 years. Special warranties are available only when the roof system is applied by a BASF Approved Applicator in strict accordance with BASF's application specifications for the particular warranty package selected. If no special warranty is purchased, BASF's Standard Product Warranty applies. For details on all available warranties, contact your BASF Roofing Specialist.

**Important!** The information, data and products presented herein are based upon information reasonably available to BASF at the time of publication, and are presented in good faith, but are not to be construed as guarantees or warranties, express or implied, regarding performance, results to be obtained from comprehensiveness merchantability, or that said information, data or products can be used without infringing patents of third parties. You should thoroughly test any application, and independently determine satisfactory performance before commercialization.

Certifications, approvals and listings are based on a specific design configuration and should be verified with BASF.

ELASTOCOAT™ is a trademark of BASF Corporation



While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

Revision Date: January 7, 2011

Page 2 of 2