



Lupranate[®] 5380 Isocyanate

Lupranate 5380 Isocyanate is a prepolymer based on carbodiimide modified MDI chemistry. The formulation of Lupranate 5380 provides the low viscosity and physical properties required for high-quality, fixed-ratio spray applications.

TYPICAL PROPERTIES

Appearance	light yellow liquid
NCO content, wt%	19.8
Viscosity @ 25°C, cps	525
Flash point, °C (COC)	> 200
Density @25°C, g/cm³	1.17
Initial boiling point, 5mm Hg, °C	200
Vapor Pressure @25°C, mm Hg	< 0.0002
Polymer Solids, wt%	< 95

Storage

Lupranate 5380 Isocyanate is supplied in tank trucks, totes, or drums. Once a container has been opened, care should be taken to exclude moisture. The most favorable temperature for storage is 20-30°C. If stored at higher temperatures, or if moisture is not excluded, an undesirable increase in viscosity will occur. Below 20°C solid crystals may form and settle out, which can alter the performance of the product. The solid crystals contain pure MDI and in this solid form may exhibit the same dimerization characteristics as pure MDI. Unless prompt action is taken to melt the product, subsequent dimerization will proceed and may deteriorate the clarity and assay of the product. Melting the crystals is done by rolling the drum in a hot air oven at 70-90°C while keeping the drum contents below 60°C to minimize dimer formation.

Warning

Excessive heating or prolonged heating at 80-100°C may cause dangerous pressure build-up. Heating by electrical means is not recommended due to the danger of local overheating, which would result in dimer formation. Melting in a water bath is not recommended because of potential danger of the isocyanate reacting with water in case of drum leakage. Rolling the drum in atmospheric steam is an alternative procedure that can be used providing care is taken to ensure that the drum does not leak. The shelf life of Lupranate 5380 Isocyanate is six months if the temperature is maintained at 20-30°C and moisture is excluded.

In case of chemical emergency:

Call CHEMTREC 800-424-9300 or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703) 527-3887.

Attention:

This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by telephoning BASF Corporation, Urethane Customer Service at (877) 297-3322 or faxing (734) 324-6866.

Important:

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue

Wyandotte, MI 48192

Phone: (734) 324-6100

<https://polyurethanes.basf.us/>