



# Pluracol® 5132

## Slabstock HR & Molded Graft Polyol

Pluracol 5132 polyol is a primary hydroxyl-terminated graft polyether triol containing approximately 32% solids of copolymerized styrene and acrylonitrile, utilizing a LVI inhibitor package. Pluracol 5132 can be used in combination with Pluracol 1603 to produce HR slabstock foams having a narrow spread in cross-sectional density and IFD properties and allows foam manufacturers to adjust the solids levels to specific formulations. Broad processing latitude permits the manufacture of a wide variety of high resilient foams. Pluracol 5132 polyol can also be used in molded foam applications.

### TYPICAL PROPERTIES

<b>Appearance</b> .....	creamy, opaque liquid
<b>Hydroxyl number, mg KOH/g</b> .....	20.8 – 22.8
<b>Water wt.% maximum</b> .....	0.05
<b>Nominal functionality</b> .....	3
<b>Density, lbs/gal @ 77°F</b> .....	8.70
<b>104°F</b> .....	8.58
<b>Viscosity, cps @ 77°F</b> .....	3500
<b>104°F</b> .....	1500
<b>Specific heat, BTU/lb °F</b> .....	0.5
<b>Thermal conductivity, BTU/hr ft<sup>2</sup> °F/in</b> .....	0.087

### Storage

Pluracol 4600 should be stored under dry conditions below 130°F.

### Shipping information

20,000-gallon tank cars, 6,000-gallon tank trucks and 55-gallon nonreturnable steel drums are standard.

### In case of chemical emergency:

Call CHEMTREC 800-424-9300 or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703) 527-3887.

### Warning

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

### Attention:

This product is sold solely for use by industrial institutions. Refer to our Material Safety Data Sheet (MSDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An MSDS as well as additional information on BASF urethane chemicals may be obtained by telephoning BASF Corporation, Urethane Customer Service at (877) 297-3322 or faxing (734) 324-6866.

### **Important:**

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

#### **BASF Corporation**

1609 Biddle Avenue

Wyandotte, MI 48192

Phone: (734) 324-6100