

Lupranate[®] M20 Isocyanate

Polymethylene Polyphenylpolyisocyanate

Lupranate[®] M20 Isocyanate is a polymeric MDI with a functionality of approximately 2.7. Lupranate[®] M20 Isocyanate can be used for the production of rigid insulation foams by molding, spraying, and frothing. It is also used for rigid and semi-flexible integral skin foams, adhesives, sealants, elastomers, and high-resiliency flexible foams. In low catalyzed rigid urethane formulations, the foam rise time can be lengthened by 20-30%. The slower reactivity can be advantageous in applications such as large rigid foam panels or molded flexible foams.

TYPICAL PROPERTIES

Appearance	dark brown liquid
Viscosity @ 25°C, cps	200
Flash point, °C (COC)	200
Density @ 25°C, g/cm ³	1.23
Initial boiling point, 5mm Hg, °C	190
Nominal functionality	2.7
Vapor Pressure @ 25°C, mm Hg	0.0002
NCO content, wt. %	31.5
Hydrolyzable chlorine, ppm	< 250



BASF Corporation is fully committed to the Responsible Care[®] initiative in the USA, Canada, and Mexico. For more information on Responsible Care[®] go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue
Wyandotte, MI 48192

Phone: 734-324-6100

<https://polyurethanes.basf.us>

Lupranate[®] M20 Isocyanate

Polymethylene Polyphenylpolyisocyanate

STORAGE

Lupranate[®] M20 Isocyanate is supplied in tank cars, tank trucks, and drums. Once a container has been opened, care should be taken to exclude moisture. The most favorable temperature for storage is 15-35°C. If stored at higher temperatures, or if moisture is not excluded, an undesirable increase in viscosity will occur. Below 15°C, the product becomes difficult to pump and pour. Below 0°C, crystallization may occur. The shelf life of Lupranate[®] M20 Isocyanate is nine months if the temperature is maintained at 15-35°C and moisture is excluded.

WARNING

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.