

## Lupranate<sup>®</sup> M70L BMBcert<sup>™</sup> M1 Isocyanate

Polymethylene Polyphenylpolyisocyanate ISCC PLUS and REDcert<sup>2</sup> Certified



Mass balanced products support and accelerate the substitution of virgin/fossil feedstock with alternative feedstock. BMB products offer the same chemical properties as their conventional equivalents but contribute to saving conventional resources and contribute to reducing  $CO_2$  emissions.

Lupranate M70L BMBcert M1 Isocyanate is a solvent-free, medium-viscosity polymethylene polyphenypolyisocyanate. Lupranate M70L BMBcert M1 Isocyanate, having a higher viscosity than Lupranate M20, is particularly suitable for the production of isocyanurate foams.

### **TYPICAL PROPERTIES**

Appearance	dark brown liquid
NCO content, wt%	31.0
Viscosity @ 25°C, cps	700
Flash point, °C (COC)	200
Density @ 25°C, g/cm3	1.23
Initial boiling point, 5mm Hg, °C	190
Nominal functionality	3
Vapor Pressure @ 25°C, mm Hg	0.00001
Hydrolyzable chlorine, ppm	150



BASF Corporation is fully committed to the Responsible Care<sup>®</sup> initiative in the USA, Canada, and Mexico. For more information on Responsible Care<sup>®</sup> go to: **U.S.**: www.basf.us/responsiblecare\_usa **Canada**: www.basf.us/responsiblecare\_canada

México: www.basf.us/responsiblecare\_mexico

#### **BASF** Corporation

1609 Biddle Avenue Wyandotte, MI 48192 Phone: 734-324-6100 https://polyurethanes.basf.us

# Lupranate<sup>®</sup> M70L BMBcert<sup>™</sup> M1 Isocyanate

Polymethylene Polyphenylpolyisocyanate

### STORAGE

Lupranate M70L BMBcert M1 Isocyanate is supplied in tank cars and tank trucks. Once a container has been opened, care should be taken to exclude moisture. The most favorable temperature for storage is 15-30°C. If stored at higher temperatures, or if moisture is not excluded, an undesirable increase in viscosity will occur. Below 15°C, the viscosity makes the product difficult to pump and pour. The shelf life of Lupranate M70L BMBcert M1 Isocyanate is nine months if the temperature is maintained at 15-30°C and moisture is excluded.

#### WARNING

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

### IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

**Important**: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.