

Lupranate® M BMBcert™ M1 Isocyanate

4,4' Diphenylmethane Diisocyanate
ISCC PLUS and REDcert² Certified



Mass balanced products support and accelerate the substitution of virgin/fossil feedstock with alternative feedstock. BMB products offer the same chemical properties as their conventional equivalents but contribute to saving conventional resources and contribute to reducing CO₂ emissions.

Lupranate M BMBcert M1 Isocyanate, a solid at room temperature, is essentially pure 4,4'-diphenylmethane diisocyanate, having a functionality of 2.0. Lupranate M BMBcert M1 Isocyanate is used in the isocyanate component for the preparation of elastomeric and thermoplastic polyurethanes, flexible and semi-flexible integral skin foams, adhesives, sealants and coatings.

TYPICAL PROPERTIES

Appearance	white to light yellow solid or liquid
Viscosity @ 25°C, cps	33
Flash point, °C (COC)	199
Density @ 25°C, g/cm ³	1.22
Initial boiling point, 5mm Hg, °C	190
Nominal functionality	2
Vapor Pressure @ 25°C, mm Hg	0.0003
NCO content, wt. %	33.5
Hydrolyzable chlorine, ppm	< 20
Purity, wt. %	99.5
2,4' Isomer, wt. %	2.0
Melting Point, °C	38.5



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
 1609 Biddle Avenue
 Wyandotte, MI 48192
 Phone: 734-324-6100
<https://polyurethanes.basf.us>

Lupranate[®] M BMBcert[™] M1 Isocyanate

4,4' Diphenylmethane Diisocyanate

STORAGE

Lupranate M BMBcert M1 Isocyanate is available in liquid form in heated tank trucks or as a solid in drums. The product is moisture sensitive and will yellow when exposed to air, especially under the influence of light. Liquid Lupranate M BMBcert M1 Isocyanate should be stored within the relatively narrow temperature range of approximately 40-50°C under nitrogen for approximately 14 days. It can be stored as a solid below 5°C. Under this cold condition and if moisture and air are excluded, the product is storage stable for up to 6 months. If stored at temperatures other than those cited, dimer formation will be excessive affecting the performance of the product. At room temperature Lupranate M BMBcert M1 Isocyanate slowly forms solid dimer of diphenylmethane diisocyanate which appears as turbidity or sediment after melting. This sediment cannot be resolubilized during later processing. Therefore, storage at room temperature is not recommended. If Lupranate M BMBcert M1 Isocyanate is stored as a solid, melting for use is done by rolling the drum in a hot air oven at 80-100°C. The drum contents should not be heated above 70°C to minimize dimer formation.

WARNING

Heating by electrical means is not recommended due to the danger of local overheating, which would result in dimer formation. Melting Lupranate M BMBcert M1 Isocyanate in a water bath is not recommended because of potential danger of the isocyanate reacting with water in case of drum leakage. Rolling the drum in atmospheric steam is an alternate procedure that can be used provided that care is taken to ensure that the drum does not leak.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.