

## Lupranate<sup>®</sup> MP102

Modified MDI

Lupranate<sup>®</sup> MP102 Isocyanate is a liquid, modified short chain prepolymer based on pure 4,4'-diphenylmethane diisocyanate (MDI). Lupranate<sup>®</sup> MP102 Isocyanate is used in conjunction with high molecular weight and reactive polyether polyols for the manufacture of high-quality flexible and semi-flexible elastomers and integral skin foams. It is especially suitable for use in the manufacture of polyurethane shoe soles. For some semi-flexible and integral skin foam applications, Lupranate<sup>®</sup> MP102 Isocyanate can be blended with polyisocyanates such as Lupranate<sup>®</sup> M20 isocyanate. It is often used in mixtures with Lupranate<sup>®</sup> MM103 isocyanate for large automotive moldings.

### TYPICAL PROPERTIES

Appearance	colorless liquid
Viscosity @ 25°C, cps	700
Flash point, °C (COC)	> 200
Density @ 25°C, g/cm <sup>3</sup>	1.21
Initial boiling point, 5mm Hg, °C	190
Nominal functionality	2
Vapor Pressure @ 25°C, mm Hg	0.0002
Hydrolyzable chlorine, wt. %	< 500
NCO content, wt. %	23.0



BASF Corporation is fully committed to the Responsible Care<sup>®</sup> initiative in the USA, Canada, and Mexico. For more information on Responsible Care<sup>®</sup> go to:

**U.S.:** [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

**Canada:** [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

**México:** [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

#### **BASF Corporation**

1609 Biddle Avenue  
Wyandotte, MI 48192

Phone: 734-324-6100

<https://polyurethanes.basf.us>

# Lupranate<sup>®</sup> MP102

## Modified MDI

### STORAGE

Lupranate<sup>®</sup> MP102 Isocyanate is supplied in tank trucks or drums. Once a container has been opened, care should be taken to exclude moisture. The most favorable temperature for storage is 25-35°C. If stored at higher temperatures, or if moisture is not excluded, an undesirable increase in viscosity will occur. Below 20°C solid crystals may form and settle out, which can alter the performance of the product. The solid crystals contain pure MDI and in this solid form may exhibit the same dimerization characteristics as pure MDI. Unless prompt action is taken to melt the product, subsequent dimerization will proceed and may deteriorate the clarity and assay of the product. Melting the crystals is done by rolling the drum in a hot air oven at 80-100°C. The drum contents should not be heated above 70°C to minimize dimer formation.

### WARNING

Heating by electrical means is not recommended due to danger of local overheating, which would result in dimer formation. Melting in a water bath is not recommended because of potential danger of the isocyanate reacting with water in case of drum leakage. Rolling the drum in atmospheric steam is an alternate procedure that can be used provided care is taken to ensure that the drum does not leak. The shelf life of Lupranate<sup>®</sup> MP102 is six months if the temperature is maintained at 25-35°C and moisture is excluded.

### IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

---

**Attention:** This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting [polyurethanes.basf.us](http://polyurethanes.basf.us).

**Important:** While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.