



Lupranate® T80 Type 1 BMBcert™ M1 Isocyanate

Toluene Diisocyanate
ISCC PLUS and RedCert² certified



Mass balanced products support and accelerate the substitution of virgin/fossil feedstock with alternative feedstock. BMB products offer the same chemical properties as their conventional equivalents but contribute to saving conventional resources and contribute to reducing CO₂ emissions.

Lupranate T80 Type 1 BMBcert M1 Isocyanate is an 80% - 20% mixture of the 2,4 and 2,6 isomers of toluene diisocyanate (TDI). This product is used in the preparation of polyurethane foams, prepolymers and elastomers.

TYPICAL PROPERTIES

NCO content, wt.%	48.2
Molecular weight	174.2
Specific gravity 25°C/25°C	1.22
Density @20°C, lbs/gal	10.2
Boiling point, 10 mm Hg, °F	248
Flash point, °F (COC)	270
Vapor Pressure @20°C, mm Hg	0.01
Freezing point, °F	53.6
Assay, % by weight minimum	99.5
Total acidity as HCl,	0.002-0.005
Hydrolyzable chloride, wt. %	0.007 max.
Isomer ratio - 2,4 wt. %	80 ± 1
- 2,6 wt. %	20 ± 1
Color, APHA, maximum	15

Storage

Store under a dry air (-20°C dew point) or dry nitrogen blanket to exclude moisture. The most favorable storage temperature for Lupranate T80 Type 1 BMBcert M1 Isocyanate is between 60°F and 95°F (15.6°C-35°C). Storage above 95°F for extended periods may cause a change in product quality. Below 60°F Lupranate T80 Type 1 BMBcert M1 Isocyanate may begin to freeze. If freezing or partial freezing occurs slowly heat the product to 60-95°F to re-liquefy. The product must be thoroughly mixed before using to ensure uniform isomer distribution and reactivity. The shelf life of Lupranate T80 Type 1 BMBcert M1 Isocyanate is twelve months if the temperature is maintained at 15-30°C and moisture is excluded.

Shipping Information

20,000-gallon tank cars, 4,500-gallon tank trucks and 55-gallon non-returnable steel drums are standard.

In case of chemical emergency

Call CHEMTREC 800-424-9300 or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703) 527-3887.

Attention

This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© BASF Corporation, 2024



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue
Wyandotte, MI 48192
polyurethanes.basf.us