



# Lupranate<sup>®</sup> T80 – Type 2

## Toluene Diisocyanate

Lupranate T80 toluene diisocyanate (TDI) is an acidified 80% - 20% mixture of the 2,4 and 2,6 isomers of toluene diisocyanate. This product is generally used in the preparation of polyurethane prepolymers.

### TYPICAL PROPERTIES

NCO content, wt.% .....	48.2
Molecular weight .....	174.2
Specific gravity 25°C/25°C .....	1.22
Density @20°C, lbs/gal .....	10.2
Boiling point, 10 mm Hg, °F .....	248
Flash point, °F (COC) .....	270
Vapor Pressure @20°C, mm Hg .....	0.01
Freezing point, °F .....	53.6
Assay, % by weight minimum .....	99.5
Total acidity as HCl, .....	0.007-0.009
Hydrolyzable chloride, wt. % .....	0.008-0.012
Isomer ratio - 2,4 wt. % .....	80 ± 1
- 2,6 wt. % .....	20 ± 1
Color, APHA, maximum .....	15

### Storage:

Store under a dry air (-20°C dew point) or dry nitrogen blanket to exclude moisture. The most favorable storage temperature for Lupranate T80 Isocyanate is between 60°F and 95°F (15.6°C-35°C). Storage above 95°F for extended periods may cause a change in product quality. Below 60°F Lupranate T80 Isocyanate may begin to freeze. If freezing or partial freezing occurs slowly heat the product to 60-95°F to re-liquefy. The product must be thoroughly mixed before using to ensure uniform isomer distribution and reactivity. The shelf life of Lupranate T80 Isocyanate is twelve months if the temperature is maintained at 15-30°C and moisture is excluded.

### Shipping Information:

20,000-gallon tank cars, 4,500-gallon tank trucks and 55-gallon non-returnable steel drums are standard.

### In case of chemical emergency:

Call CHEMTREC 800-424-9300 or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703) 527-3887.

### **Attention:**

This product is sold solely for use by industrial institutions. Refer to our Material Safety Data Sheet (MSDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An MSDS as well as additional information on BASF urethane chemicals may be obtained by telephoning BASF Corporation, Urethane Customer Service at (877) 297-3322 or faxing (734) 324-6866.

### **Important:**

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

#### **BASF Corporation**

1609 Biddle Avenue

Wyandotte, MI 48192

Phone: (734) 324-6100