

Lupranate® T80– Type 2

Toluene Diisocyanate

Lupranate T80 toluene diisocyanate (TDI) is an acidified 80% - 20% mixture of the 2,4 and 2,6 isomers of toluene diisocyanate. This product is generally used in the preparation of polyurethane prepolymers.

TYPICAL PROPERTIES

| | |
|-------------------------------|-------------|
| NCO content, wt% | 48.2 |
| Flash point, °C (COC) | 270 |
| Boiling point, 10 mm Hg, °F | 248 |
| Nominal functionality | 2 |
| Vapor Pressure @ 20°C, mm Hg | 0.01 |
| APHA Color, maximum | 15 |
| 2,4' Isomer, wt. % | 80 ± 1 |
| 2,6' Isomer, wt. % | 20 ± 1 |
| Hydrolyzable chlorides, wt. % | 0.008-0.012 |
| Total acidity as HCl | 0.007-0.009 |
| Freezing point, °F | 53.6 |
| Density @20°C, lbs/gal | 10.2 |
| Molecular weight | 174.2 |
| Specific gravity 25°C/25°C | 1.22 |
| Assay, % by weight minimum | 99.5 |



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue
Wyandotte, MI 48192

Phone: 734-324-6100

<https://polyurethanes.basf.us>

Lupranate® T80– Type 2

Toluene Diisocyanate

STORAGE

Store under a dry air (-20°C dew point) or dry nitrogen blanket to exclude moisture. The most favorable storage temperature for Lupranate T80 Isocyanate is between 60°F and 95°F (15.6°C-35°C). Storage above 95°F for extended periods may cause a change in product quality. Below 60°F Lupranate T80 Isocyanate may begin to freeze. If freezing or partial freezing occurs slowly heat the product to 60-95°F to re-liquefy. The product must be thoroughly mixed before using to ensure uniform isomer distribution and reactivity. The shelf life of Lupranate T80 Isocyanate is twelve months if the temperature is maintained at 15-30°C and moisture is excluded.

Shipping I

SHIPPING INFORMATION

20,000-gallon tank cars, 4,500-gallon tank trucks and 55-gallon non-returnable steel drums are standard.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.