

Lupraphen® 1613/1

Polyester Polyol

Lupraphen 1613/1 is a polyethylene/propylene adipate with a molecular weight of 2000. It is often used in high property polyurethane elastomers, elastomeric coatings and adhesives applications.

TYPICAL PROPERTIES

Appearance	white to pale yellow waxy solid
Hydroxyl number, mg OH/g	52.0–58.0
Water wt.% maximum	0.05
Acid number, maximum	0.7
Viscosity @ 60 °C, cps	900–1150
Color, APHA maximum	75
Nominal functionality	2
OH number (avg)	55
Nominal molecular weight	2000
Specific gravity @ 25 °C	1.19



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue
Wyandotte, MI 48192

Phone: 734-324-6100

<https://polyurethanes.basf.us>

Lupraphen® 1613/1

Polyester Polyol

STORAGE

Lupraphen 1613/1 containers should be kept tightly closed away from moisture and foreign materials. It is hygroscopic and tends to absorb water which may adversely affect processing. Use of a dry nitrogen blanket for partial drums is recommended. Storage temperatures should be maintained at room temperature or higher, not to exceed 75 °C. Maintaining proper storage conditions, the shelf life of the material is 24 months.

SHIPPING INFORMATION

6,000-gallon tank trucks and 55-gallon nonreturnable steel drums are standard.

WARNING

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.