



Pluracol[®] 1026

Molded Foam Polyol

Pluracol 1026 polyol is a high molecular weight triol developed for the manufacture of high resiliency molded foams. HR foams made with Pluracol 1026 in combination with graft polyols, such as Pluracol 4830, process well and are easily crushed.

TYPICAL PROPERTIES

Appearance	clear liquid
Hydroxyl number, mg KOH/g	26.5 – 28.5
Water wt.% maximum	0.05
Acid number, maximum	0.01
Na & K, ppm maximum	5
Color, APHA maximum	30
Unsaturation, meq/g maximum	0.06
Nominal functionality	3
Nominal molecular weight	6000
Density, lbs/gal @ 70°F	8.57
100°F	8.45
120°F	8.32
Viscosity, cps @ 70°F	1329
100°F	650
120°F	350
Specific heat, BTU/lb °F	0.5
Thermal Conductivity, BTU/hr ft² °F/in	0.087

Storage

Pluracol 1026 should be stored under dry conditions below 140°F.

Shipping information

20,000-gallon tank cars, 6,000-gallon tank trucks and 55-gallon nonreturnable steel drums are standard.

In case of chemical emergency:

Call CHEMTREC 800-424-9300 or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703) 527-3887.

Warning

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

Attention:

This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by telephoning BASF Corporation, Urethane Customer Service at (877) 297-3322 or faxing (734) 324-6866.

Important:

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.

Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue

Wyandotte, MI 48192

Phone: (734) 324-6100

<https://polyurethanes.basf.us/>