

Pluracol® 628

Specialty Polyol

Pluracol 628 polyol is a high molecular weight, primary hydroxyl terminated diol used in the manufacture of polyurethane shoe soles and fascia products. Pluracol 628 can also be used to manufacture a variety of sealants and elastomers.

TYPICAL PROPERTIES

Appearance	clear liquid
Hydroxyl number, mg OH/g	24.5–26.5
Water wt.% maximum	0.05
Acid number, maximum	0.01
Na & K, ppm maximum	5
Color, APHA maximum	30
Nominal functionality	2
OH number (avg)	25
Nominal molecular weight	3850
Specific gravity @ 25 °C	1



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue
Wyandotte, MI 48192

Phone: 734-324-6100

<https://polyurethanes.basf.us>

Pluracol® 628

Specialty Polyol

STORAGE

Pluracol® 628 should be stored under dry conditions below 60 °C. Maintaining proper storage conditions, the shelf life of the material is 24 months.

SHIPPING INFORMATION

20,000-gallon tank cars, 6,000-gallon tank trucks and 55-gallon nonreturnable steel drums are standard.

WARNING

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.