

Technical Data Sheet

TDA (m-TDA)

Toluene Diamine

Toluene Diamine or m-TDA, is a mixture of 2,4- and 2,6-isomers.

TYPICAL PROPERTIES

Isomers Purity	Min 99.1%
2,4 TDA Isomer, Normalized	79.0 - 81.0%
2,6 TDA Isomer, Normalized	19.0 - 21.0%
Water	Max 500 ppm
Total other isomers	Max 0.11%
Toludines	Max 0.1%



BASF Corporation is fully committed to the Responsible Care[®] initiative in the USA, Canada, and Mexico. For more information on Responsible Care[®] go to:

U.S.: www.basf.us/responsiblecare_usaCanada: www.basf.us/responsiblecare_canadaMéxico: www.basf.us/responsiblecare_mexico

BASF Corporation

1609 Biddle Avenue Wyandotte, MI 48192 Phone: 734-324-6100 https://polyurethanes.basf.us 30230682 Page 2 of 2

TDA (m-TDA)

Toluene Diamine

STORAGE

Storage of the TDA should be under inert atmosphere. Aromatic amines should not be exposed to oxygen, they readily oxidize and degrade in the presences of oxygen. The most favorable storage temperature for TDA is between 61°C and 93°C (142°F-199°F). Storage above 93°C for extended periods may cause a change in product quality. Below 61°C TDA may begin to freeze. If freezing or partial freezing occurs slowly heat the product to 61-93°C to reliquefy. The product must be thoroughly mixed before using to ensure uniform isomer distribution and reactivity. The shelf life of TDA is twelve months if the temperature is maintained at 61-93°C and an inert atmosphere is maintained.

SHIPPING INFORMATION

4,500-gallon tank trucks or isotainers are standard.

IN CASE OF CHEMICAL EMERGENCY

Call CHEMTREC (800-424-9300) or BASF (800-832-HELP) day or night for assistance and information concerning spilled material, fire, exposure and other chemical accidents. Outside the U.S., call (703-527-3887).

Attention: This product is sold solely for use by industrial institutions. Refer to our Safety Data Sheet (SDS) regarding regulatory compliance, safety, hazards, spill procedures and disposal of this product. An SDS as well as additional information on BASF urethane chemicals may be obtained by visiting polyurethanes.basf.us.

Important: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

©BASF Corporation, 2025 January, 2025